ComfortDOME FM5

Conductive Dome ESD Anti-Fatigue Mat

Energizing dome mat provides unparalleled comfort in areas where static is a concern .

The ComfortDOME flooring system is a range of individual mats and modular flooring that offers a unique combination of proven ergonomic and heath benefits plus ESD protection.

Evenly spaced ComfortDOMES on the conductive surface of the mat provides superior anti-fatigue relief because ComfortDomes get softer as compressed, not harder like products made with foam. ComfortDOMES recover/rebound more rapidly than most foam resulting in an energizing responsiveness not found in other mats. Available in single work area mats or in interlocking sections for long assembly lines.

Meets or exceeds requirements of ANSI ESD-S20.20 and the recommendations of ESD STM7.1.



ComfortDOMES function like a spring to return energy. The unique "air pocket" structure becomes softer as compressed. ComfortDOMES rebound instantly as weight is shifted.

Specifications: Part Numbers

damage

specifications.		rait ivuilibeis.	
Tensile Strength	9.95	FM52X3	2' x 3'x1/2" Mat
Elongation @ Break%	475	FM53X5	3' x 5'x1/2", Mat
Abrasion/mm3	170	FM53X4IC	3' x 4'x1/2", Runner,
Hardness (shore A)	50 +/- 5		Center Piece
Specific gravity	1.33 +/-0.05	FM53X4EP	3' x 4'x1/2", Runner,
Tear Strength/Nmm-1	89.5		End Piece
Heat Resistant	No visual		

Compression 20%
Skid (Slip) Resistant 35 BPM
Point to Point Resistance 10^3 - 10^5





Features

- Provides an Anti-Fatigue, Energizing
 Surface to Stand On.
- Available in Workstation Mats, or
 Interlocking Mats for Long Runners
- 100% Conductive Rubber Complies
 with ANSI ESD20.20

Applications:

ESD Anti-fatigue mats provide a path-toground for workers wearing ESD footwear as well as reduce worker discomfort from standing for long periods

This document is prepared for our customers as a service, and is to the best of our knowledge true and accurate. However, it is understood and agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.