## VME Series Three Layer ESD Vinyl Table Mat

## Protect your sensitive items as well as your work surface with shock absorbing ESD matting.

Designed for use at workstations and other manufacturing areas, the three layer VME Vinyl serves a dual purpose: the closed-cell foam absorbs and reduces the shock and impacts associated with manufacturing electronic equipment such as disk drives and hard drives, while also dissipating static through immediate touch prior to handling such static-sensitive equipment. Made from two layers of polyvinyl chloride foam that encase a layer of conductive fleece to form an expanded static dissipative work surface.

Resistant to degradation by inorganic acids, organic acids, reducing agents, detergent solutions, alcohols, aliphatic hydrocarbons, mineral oil, and aldehydes.

Meets or exceeds requirements of ANSI ESD-S20.20 and the recommendations of ESD 4.1.



## **Features**

- Three Layer Vinyl: 10^7—9 x 10^8 Rtt
- Absorbs and reduces high impacts risk of electrical shock
- Available in 60ft rolls or an Assortment of cut to order table mats
- Available in light blue color

## **Applications:**

Creates an ESD safe work area by a providing a path-to-ground for electrical charges as well as protecting the work surface from damage.

| Specifications:  |                                       | Part Numbers: |                                      | Part Numbers:    |                                  |
|--|---------------------------------------|---------------|--------------------------------------|------------------|----------------------------------|
| Thickness  | 0.375"                                | Full Rolls    |                                      | Cut Mats         |                                  |
| Color  | Blue                                  | VME2460B      | Roll, Light Blue, 24" x 60' x .375"  | VME2436C         | Mat, 24" x 36"x .375", Hardware  |
| Emboss Pattern   | Matte finish (non-embossed)           | VME3060B      | Roll , Light Blue, 30" x 60' x .375" | VME2448C         | Mat, 24" x 48"x .375" , Hardware |
| Gauge  | 0.375" +/040"                         | VME3660B      | Roll, Light Blue, 36" x 60' x .375"  | VME2460C         | Mat, 24" x 60"x .375" , Hardware |
| Density  | 25 lb/ft³ nominal <i>wear layer</i>   |               |                                      | VME3048C         | Mat, 30" x 60" x .375", Hardware |
|  | 18 lb/ft³ nominal <i>bottom layer</i> |               |                                      | VME3072C         | Mat, 24" x 72"x .375" , Hardware |
| Tensile  | 100 lb/in² minimum                    |               |                                      | VME3648C         | Mat, 36" x 48"x .375" , Hardware |
| Elongation   | 100% minimum                          |               |                                      | VME3672C         | Mat, 36" x 72"x .375" , Hardware |
| Tear   | 20 lb/in minimum                      |               |                                      |                  |                                  |
| Durometer  | 70 +/- 5, Shore OO                    |               | Shipping Dimensions and Weights      |                  |                                  |
| Worksurface  | 1.0 x 10^7—9.0 x 10^8 Ω               | ESD S4.1-1997 |                                      | Roll, 24" x 60': | 81lbs - 20"W x 20"H x 26"L       |
|  |                                       |               |                                      | Roll, 30" x 60': | 100lbs - 20"W x 20"H x 32"L      |
| The ESD matting is rated to 200F (93C). The mats are heat resistant, not heat proof. They will withstand Roll, 36" x 60': 120lbs - 20"W x 20"H x 38"L exposure to high temperatures, but it is dependant on exposure time. |                                       |               |                                      |                  |                                  |

This document is prepared for our customers as a service, and is to the best of our knowledge true and accurate. However, it is understood and agreed by the users of this document that we will accept no liability for the conclusions reached. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.